SUZORITE® 150-S

IMERYS Suzorite[®] 150-S phlogopite mica is a flake & powder product which is processed in Boucherville, Quebec.

Manufacturers specify phlogopite mica for applications requiring reinforcement and where greater resistance to moisture, heat, light or chemicals is needed. As a platy mineral, Imerys phlogopite mica offers beneficial rheological properties, is chemically inert, and provides the highest thermal stability of any mica. These properties render Imerys phlogopite micas excellent functional minerals for plastic composites, sound deadening, foundry coatings, and many other applications.


IMERYS Suzorite 150-S mica has a high aspect ratio and is used in a broad range of applications, including:

 Plastic Composites: Substantially increases stiffness and heat resistance, while promoting dimensional stability and improving electrical insulation properties.

TYPICAL PROPERTIES

Source	Boucherville, Quebec, Canada
Median Particle Size (µm)	150
Aspect Ratio (Jennings)	90
Moisture (@100° C) (wt.%)	<0.5
Density:	
Bulk (lbs/ft.³)	14
Specific Gravity	2.73
Loss On Ignition (@ 1000°C) (wt.%) <1.0
pH	9.2
Hardness (Mohs)	3
Refractive Index	1.58

TYPICAL PARTICLE SIZE DISTRIBUTION*



^{*} By Cilas Laser Light Scattering: Actual test results may vary. Provisional Specifications.



PART IS A CONTRACT OF PART





July 2012 ©IMERYS 2012 Sixth Edition All products are registered trademarks of IMERYS

CAS No. 12001-26-2

IMERYS 100 Mansell Court East Suite 300 Roswell, GA 30076

General: Tel: (770) 594.0660 Fax: (770) 645.3384 www.imerys-perfmins.com

> Customer Service: Tel: (888) 277.9636 Fax: (770) 645.3631

IMERYS is a business name of IMERYS Pigments, Inc., IMERYS Kaolin, Inc., IMERYS Mica Suzzorite, Inc. and IMERYS Marble, Inc. Registered in the USA.

This information is believed to be correct. However, this information does not constitute any representation, condition or warranty, nor do we guarantee results to be obtained. All recommendations and ales are made on the condition that we will not be held liable for any damages resulting from their use. This provision may not be changed by any of our representatives.

